

HA 7115

Ni 15.5Cr 4.3Si 4Fe 3.5B

Product Code: 257256-1
Technical Data Sheet

Revision: # 001
 Dated: 05/05/10




Figure 1: Typical Powder Morphology (SEM 100X)

1. PHYSICAL PROPERTIES

HA 7115 is a self-fluxing, Nickel Chrome hard facing alloy powder produced by an atomization process. It produces very dense and corrosion resistant coatings, which resist wear by abrasive grains, hard surfaces, particle erosion and cavitation, in both low and high temperatures. As a self fluxing alloy it is designed to be “fused” or re-melted in a normal atmosphere after being sprayed. They then coalesce into a dense, essentially pore-free coating with a hardness of 55 – 60 HRc. HA 7115 meets, and exceeds, AMS Specification 4775A.

Molecular Formula	Ni 15.5Cr 4.3Si 4Fe 3.5B
Melting Point [°C]	960 - 1030
Hall Flow [s/50g] ASTM B213	15 ± 2
Apparent Density [g/cm³] ASTM B212	4.0 ± 0.5

HA 7115

Ni 15.5Cr 4.3Si 4Fe 3.5B

Product Code: 257256-1
Technical Data Sheet

Revision: # 001
Dated: 05/05/10

2. CHEMICAL PROPERTIES

2.1. Typical Chemical Analysis*

<u>Element</u>	<u>Weight Percent</u>
Nickel [Ni]	65 - 75
Chromium [Cr]	13 - 20
Iron [Fe]	3.0 – 5.0
Carbon [C]	0.6 – 1.3
Silicon [Si]	3.0 – 5.0
Boron [B]	2.75 – 4.75
Cobalt [Co]	1.0 max.
All Others	< 1.00

*) Analysis in accordance to AMS 4775A

3. POWDER MORPHOLOGY AND PARTICLE SIZE DISTRIBUTION

3.1. Powder Morphology

- 3.1.1. Powder has a round shape as produced by atomization process.
- 3.1.2. Typical Powder Morphology using SEM is shown in Figure 1.

3.2. Particle Size Distribution

- 3.2.1. The typical powder size range measured with Tyler according to ASTM B214 is -140 mesh +325 mesh
- 3.2.2. Table 1 shows the required and typical particle size distribution measured with Microtrac according to ASTM B822
- 3.2.3. Figure 2 shows the typical Microtrac particle size distribution graph

HA 7115

Ni 15.5Cr 4.3Si 4Fe 3.5B

Product Code: 257256-1
 Technical Data Sheet

Revision: # 001
 Dated: 05/05/10

Table 1: Typical and Required Microtrac Particle Size Distribution

<u>Percentile</u>	<u>Typical Particle Size</u>		<u>Mean</u>	<u>Required Particle Size</u>
[%]	[μm]			
0.01	18.59		D ₁₀	40 - 65 μm
5.00	32.97			
10.00	40.93			
16.00	48.51		D ₅₀	70 - 95 μm
50.00	75.36			
84.00	112.4			
90.00	130.0		D ₉₀	105 - 140 μm
95.00	161.3			
99.99	349.6			




Figure 2: Typical Microtrac Particle Size Distribution